

MULTIFILL EPOXY CLEANER

Cleaning agent for epoxy grout residue

Description

Special gel cleaner, containing a mixture of solvents.

Fields of application

MULTIFILL EPOXY CLEANER is used to remove residue of hardened epoxy grout (e.g. MULTIFILL EPOXY THIXO or MULTIFILL EPOXY FLOW) from tile surfaces, due to inadequate cleaning of the grout while applying it. Suitable for horizontal and vertical surfaces.

Technical data

Form: Gel

Color: Transparent

Ph : 7,5

Density : 1,05 Kg/l

Application temperature : 5- 35 °C

Disintegration time of residue: 1-8 Hr

Directions for use

MULTIFILL EPOXY CLEANER is applied undiluted with a brush or trowel on the hardened residue of the epoxy grout and is then left to act, until it has softened the residue. This usually takes 1-8 hours, depending on the size of the residue. Finally, the residue is removed with a metal trowel and the surface is thoroughly rinsed with water. The procedure can be repeated, if necessary.

Consumption

Depending on the size of the residue that needs to be removed.

Packaging

MULTIFILL EPOXY CLEANER is available in 0.75 l containers.

Storage

24 months from production date, in places protected from high temperatures and frost.

Remarks

- Consult the directions for safe use and precautions written on the container.
- Protect surfaces that are sensitive to solvents from coming to direct contact with the cleaning agent (e.g. plastics).
- Before applying the product on polished tiles, marble or natural stone, try it first to make sure it does not change their appearance.
- Avoid contact of the cleaning agent with the tile joints, as it might damage the epoxy grout already used in the joints, in the same way it removes the grout residue from the tiles.

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

Thessaloniki: 17th km Thessaloniki - Ag. Athanasios Road, P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,

Tel.: +30 2310 576 000, Fax: +30 2310 722 475

Athens: 57th km Athens-Lamia N.R., 32011 Inofita, Greece

Tel.: +30 22620 56406 Fax: +30 22620 31644

www.isomat.eu e-mail: info@isomat.eu

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Department of Research and Development of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

