

Thick Bed FlexiRapid

Pourable and Flexible Rapid Setting Floor Tile Adhesive

- Developed for solid bed fixing of large format tiles
- Ideal for ceramic, porcelain, terrazzo and natural stone tiles
- Pourable and flexible
- Rapid setting, grout after 3 hours
- Ideal for uneven tiles and uneven surfaces
- Suitable for use over Underfloor Heating Systems
- Ideal for plywood overlay
- Internal and external use
- 3mm – 25mm bed depth

CLASS
C2 F
to EN 12004

3 - 25mm
Bed
Thickness

3 Hours
Walkable/
Groutable



TILEMASTER THICK BED FLEXIRAPID

Pourable and Flexible Rapid Setting Floor Tile Adhesive

DESCRIPTION:

Tilemaster Thick Bed FlexiRapid is a pourable and flexible rapid setting cement based floor tile adhesive. Thick Bed FlexiRapid has been specially developed for the solid bed fixing of a wide range of large format tiles such as ceramic, porcelain, terrazzo and natural stone tiles. Thick Bed FlexiRapid can be applied up to a bed thickness of 25mm. It is ideal for fixing tiles of uneven thicknesses, for fixing to uneven surfaces and it can also be used to level uneven floors. A fast track adhesive, the rapid setting properties of Thick Bed FlexiRapid allow for light foot traffic and grouting after 3 hours. Thick Bed FlexiRapid is ideal for use in areas subject to prolonged or permanent wet conditions such as wet rooms and swimming pools. The product can be used internally and externally and it is unaffected by frost after setting.

TILES:

- ✓ Ceramics
- ✓ Porcelain
- ✓ Marble
- ✓ Travertine
- ✓ Limestone
- ✓ Slate
- ✗ Quartz
- ✓ Granite
- ✗ Composite
- ✓ Terracotta
- ✓ Mosaics
- ✓ Quarry

SUBSTRATES:

- ✓ Sand/Cement Screed
- ✓ Concrete
- ✓ Plywood Overlay (15mm min)
- ✓ Chipboard Overlay (18mm min)
- ✓ Electric Underfloor Heating
- ✓ Water/Wet System Underfloor Heating
- ✓ Tile Backer Boards
- ✓ Tile on Tile
- ✓ Flooring Grade Asphalt & Bitumen
- ✓ Anhydrite Screeds
- ✗ Plaster
- ✗ Plasterboard
- ✓ Fibre Cement Sheet
- ✗ Cement/Sand Render
- ✗ Concrete Brick/Block
- ✗ T & G Floorboards
- ✗ Floating Floors
- ✓ Existing Vinyl Tiles
- ✗ Steel/Metal Surfaces
- ✗ Fibreglass
- ✗ Green Screed

PREPARATION:

Before starting, all substrates must be clean, dry and strong enough to support the weight of the tiles, tile adhesive and grout. Remove all dust, dirt, oil, grease and other contaminants that may affect adhesion.

MIXING & APPLICATION:

Only mix small quantities at a time until you have become accustomed to the fast setting nature of the product. Always mix powder to water and mix to a smooth and lump free consistency. As a guide for powder to water ratio, 20kg of powder requires approximately 3.6 – 4.0 litres of water. Never add water after initial mixing, as this will impair the strength of the adhesive. Any product that has started to set must be discarded.

Pour the adhesive from the mixing bucket onto the substrate, do not spread more adhesive than can be tiled in 15-20 minutes. Trowel the adhesive to the required depth using a suitable large format / solid bed notched trowel. Bed tiles into adhesive using a twisting action ensuring full coverage of adhesive between tile and substrate. Using the Thick Bed FlexiRapid to fix tiles with a solid bed fixing method usually removes the need to back butter large format tiles, however, adhesive should be applied to the back of deep studded tiles to cover the studs. Ensure the adhesive is still moist and there is full coverage when tiles are pressed into place with a twist action.

NB. When fixing tiles externally or in areas subject to prolonged or permanent wet conditions, you must ensure that you achieve 100% adhesive coverage between tile and substrate.

Clean surplus adhesive from the tiles and joints as soon as possible as set adhesive will prove very difficult to remove later.

Clean tools after use with water.

GROUTING:

Do not start grouting until the adhesive has set. This time can vary depending on temperature and site conditions. Impervious surfaces may extend the set time. In ideal conditions grouting can begin after 3 hours. If you are tiling an area of limited movement or underfloor heating you must use a flexible grout. Our Grout 3000 and Flexigrout range are highly recommended.

If you are unsure with any of our instructions please call our Technical Helpline on 01772 456831, we will be happy to assist.

TILEMASTER **THICK BED FLEXIRAPID**

Pourable and Flexible Rapid Setting Floor Tile Adhesive

SUBSTRATE PREPARATION GUIDE:

Concrete: New concrete must be allowed a minimum of 6 weeks drying time. As an approximate guide for drying times, allow 1 day per mm up to an overall depth of 50mm and 2 days per mm for anything above 50mm. Remove any laitance from the surface mechanically and ensure that mould oil, curing agents and any other contaminants are removed. Remove all dust and dirt ideally by vacuum. Prime the surface with Primeplus diluted 3 parts water to 1 part Primeplus and allow to dry. Very porous substrates will require more than one coat.

Sand/Cement Screed: New sand/cement screed must be left for a minimum of 4 weeks to dry sufficiently. Remove any laitance from the surface mechanically and ensure that mould oil, curing agents and any other contaminants are removed. Remove all dust and dirt ideally by vacuum. Prime the surface with Primeplus diluted 3 parts water to 1 part Primeplus and allow to dry. Very porous substrates will require more than one coat.

Flooring Grade Asphalt/Bitumen: Ensure that the flooring grade asphalt/bitumen is in good condition and that there are no signs of debonding and/or hollowness. Make sure the surface is dry and free of any contaminants, loose dust or dirt. Prime the surface with one coat of Prime + Grip and allow to dry.

Existing Ceramic, Porcelain & Natural Stone Tiles: Ensure the surface is dry and free of any contaminants, loose dust or dirt. Existing tiles that have been previously treated with sealer must be sufficiently cleaned in order to remove any surface treatments. Prime the surface with one coat of Prime + Grip and allow to dry.

Plywood Overlay: Prior to tiling, ensure that new or existing boards are dry, i.e. conditioned to the environment in which they will be used. Plywood must be 15mm (minimum), exterior grade, screwed (not nailed) to substrate at 6 inch/150mm centres. Ensure there is sufficient ventilation beneath substrate and that the plywood has been fitted competently and will take the weight of the tiles, tile adhesive and grout. Make sure the surface is dry and free of any contaminants, loose dust or dirt. The top surface of the plywood does not require priming prior to tiling. Prime the reverse side and edges of the plywood with neat Primeplus.

Chipboard Overlay: Prior to tiling, ensure that new or existing boards are dry i.e. conditioned to the environment in which they will be used. Chipboard must be a minimum of 18mm and must be screwed (not nailed) to the substrate at 6 inch/150mm centres. Ensure there is enough ventilation beneath the substrate and that the chipboard has been fitted competently and will take the weight of tiles, tile adhesive and grout. Make sure the surface is dry and free of any contaminants, loose dust or dirt. The top surface of the chipboard does not require priming prior to tiling. Prime the reverse side and edges of the chipboard with neat Primeplus.

Underfloor Heating Systems: When tiling onto existing underfloor heating you must switch the heating off 48 hours prior to tiling to allow the substrate to cool sufficiently. When tiling has been completed allow 1 week for full cure of tile adhesive and grout before switching the heating on. When doing so, start with a low temperature and gradually increase the temperature on a daily basis by no more than 2°C per day.

When tiling on to a new electric element underfloor heating system, Tilemaster Adhesives strongly recommend embedding the electric underfloor heating mat/element into a self levelling compound such as Levelflex or Rapid Level 30 in order to protect the heating element and to leave a perfect surface on which to apply tiles. Again, allow one week for full cure before switching the heating on, start with a low temperature and gradually increase the temperature on a daily basis by no more than 2°C per day.

Underfloor Heated Screeds should be commissioned prior to tiling. Turn on the heating system at a low temperature and heat the screed gradually by no more than 5°C per day until a maximum temperature of 25°C is achieved. Maintain this temperature for 3 days and then switch the heating off 48 hours prior to tiling to allow the substrate to cool sufficiently. Alternatively in cold conditions, reduce the temperature of the screed to below 15°C prior to tiling. When tiling has been completed allow 1 week for full cure of tile adhesive and grout before switching the heating on. When doing so, start with a low temperature and gradually increase the temperature on a daily basis by no more than 2°C per day.

Anhydrite/Gypsum Screed: Anhydrite/Gypsum screeds must be confirmed dry via consistent moisture readings across the whole floor. The residual moisture content of the screed must be less than 0.5%. Alternatively the relative humidity must be 75% or below. As an approximate guide for drying times, allow 1 day per mm up to an overall depth of 40mm and 2 days per mm for anything above 40mm. The drying of anhydrite/gypsum screeds can be assisted by commissioning the underfloor heating system, for further information, please contact our Technical Helpline. All anhydrite/gypsum screeds must be mechanically sanded/abraded in order to remove the laitance from the surface of the screed.

Tilemaster Adhesives recommended tile adhesive for use on anhydrite/gypsum screeds is AnhyFix. For details on tiling to anhydrite/gypsum screeds with Tilemaster Thick Bed FlexiRapid, please contact the **Technical Helpline on 01772 456831**.

Tile Backer Board: Ensure the surface is dry and free of any contaminants, loose dust or dirt. Prime the surface with one coat of Primeplus diluted 3 parts water to 1 part Primeplus and allow to dry.

Existing Vinyl Tiles/Sheet Vinyl: Make sure the existing vinyl tiles/sheet vinyl is firm, stable and well adhered to the substrate to which the vinyl was originally applied to. Ensure the surface is dry and free of any contaminants, loose dust and dirt. Prime the surface with one coat of Prime + Grip and allow to dry.

Power Floated Concrete: Ensure the surface has been allowed 7 days to cure. Power floated concrete can leave a loose top layer and/or laitance once it has cured. Remove the loose top layer and any laitance from the surface mechanically or by acid etching and remove all dust and particles ideally by vacuum. Once all laitance has been removed, prime the surface with one coat of Primeplus diluted 3 parts water to 1 part Primeplus.

TILEMASTER **THICK BED FLEXIRAPID**

Pourable and Flexible Rapid Setting Floor Tile Adhesive


Standard Conformity	Conforms to BS EN 12004 C2 F
Bed Thickness	3mm – 25mm
Coverage	20kg will cover approximately 5m ² at 3mm bed application
Open Time/Working Time	Approximately 30 minutes at 20°C
Before Grouting	Approximately 3 hours depending on temperature and substrate The set time will be increased by lower temperatures and reduced at higher temperatures * Tiling onto an impervious substrate with a non-porous tile will increase the set time
Storage	Store unopened, clear of the ground in cool, dry conditions
Shelf Life	Stored correctly this product has a shelf life of 6 months
Colours	Grey and White
Pack Sizes	20kg
Note	All work must be carried out in accordance with British Standard Code of Practice for floor and wall tiling BS5385

HEALTH AND SAFETY

Tilemaster Thick Bed FlexiRapid Adhesive contains cement. Contact with moisture or gauging water sets off an alkaline reaction which may cause skin irritation and/or caustic burns to mucous membranes (e.g. eyes). Irritant to respiratory system. Risk of serious damage to eyes, therefore avoid contact with eyes and prolonged contact with skin. Do not breathe dust. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. After contact with skin, take off immediately all contaminated clothing, and wash immediately with plenty of water and soap. Wear suitable gloves (e.g. cotton gloves soaked in nitrile) and eye/face protection. If swallowed, seek medical advice immediately and show this container or label. Keep out of reach of children. Low in chromates.

For further information refer to the Material Safety Data Sheet.

The information contained on this spec sheet is given voluntarily and in good faith. It is to the best of our knowledge true and accurate; however it may contain information which is inappropriate under certain conditions of use. The company cannot accept responsibility for any loss or damage due to inappropriate use or the possibility of variations of working conditions and of workmanship outside our control.

 15	
Tilemaster Adhesives Ltd., Unit 4, Tomlinson Point, Tomlinson Road, Leyland, Lancs, PR25 2DY	
EN 12004 Class C2 F Improved fast setting cement based adhesive	
Bond Strength, as:	
• initial tensile adhesion strength	> 1.0 N/mm ²
Durability, for:	
• tensile adhesion strength after heat ageing	> 1.0 N/mm ²
• tensile adhesion strength after water immersion	> 1.0 N/mm ²
• tensile adhesion strength after freeze/thaw cycles	> 1.0 N/mm ²

Tilemaster Adhesives Ltd.

Unit 4, Tomlinson Point, Tomlinson Road, Leyland, Lancashire, PR25 2DY.

Telephone: **0845 208 0040** Fax: **0845 208 0041**

Technical: **01772 456831**



www.tilemasteradhesives.co.uk